

Sylac

Varnish & Coatings for wooden surfaces

Sylaqua Parquet Topcoat P780/xx

Datum revizije: 07/07/2020

Detalji proizvoda

Naziv proizvoda - Kod	Sylaqua Parquet Satin P-780/xx (xx: 10, 20, 30, 40, 50, 60, 70, 80)
Tip proizvoda	1 Komponentni PU završni premaz za parket (drvo) na bazi vode
Aplikacija	Unutrašnje drvene površine
Opis	Transparentni završni premaz za završnu obradu drvene površine parketa • Otpornost na habanje za parket sa velikim prometom • Protok koji poboljšava lakoću primene • Otporan na ogrebotine, vrhunska otpornost na habanje, održavajući sjaj premaza • Sadrži nanočestice koje nude povećanu izdržljivost • Izgled svilenog satena • Jasnoća koja naglašava prirodan osećaj zrna drveta • Visoka hemijska otpornost • 100% PU - Ne žuteći

Tehnički podaci

Sjajnost (60°)	(xx: 10, 20, 30, 40, 50, 60, 70, 80) ±5 (EN ISO 2813:1994)
Čvrste materije	31.5 % ±1 (EN ISO 3251:2003)
Viskoznost	Brookfield (50 RPM, 20 °C): 430 cPs ± 100 (EN ASTM D 2196)
Taber abrazija (CS10, 1000 cycles, 1KG)	100 mg
Adhezija	CAT 0 ±1(EN ISO 2409:1992)

Informacije o proizvodu

Aplikacija i uslovi sušenja	Uvek iznad 12° C.
Skladištenje	Proizvod ne treba čuvati ispod 5° C i iznad 40° C.
Preporučena težina aplikacije	140-180 g/m²
Suvo na dodir	45 min na 23 °C, 50% RH (100 g/m²)
Aparat za aplikaciju	Roler, Četka, Pnaumatski pištolj, Airless pištolj.
Pakovanje	1 L, 5 L,
Rok Trajanja	12 meseci. Nakon dužeg perioda skladištenja obezbedite homogenost proizvoda tako što ćete dobro promešati pre upotrebe da biste uklonili eventualni sediment.

Aplikacija

Priprema	Obrusite i očistite drvenu površinu od prašine, prljavštine, masti ili voska. Pre aplikacije <i>Sylaqua P-780/xx</i> , drvenu površinu treba zapuniti osnovnim premazom, tip P-280.		
Odnos mešanja	Proizvod	(kg)	(L)
	P-780/xx	100	100
	DI voda	10-25	10-25
Aplikacija	Korak 1: Dobro promešajte proizvod da biste obezbedili ujednačenu konzistenciju. Razblažite od 10-25% with destiliranom vodom. Korak 2: Korišćenjem valjka, četke ili pištolja za prskanje sa diznom od 1,8-2,0 mm ili airless pištolja sa 1.1mm diznom. Nanesite jedan film proizvoda kojim ćete premazati površinu drveta 100 - 150 a/m².		

The above information is given in good faith based on everything we know about the specific product. Every applier must take upon him to test the above information according to their personal work requirements before the application of the product. Sylac S.A. does not carry any responsibility for any damage that can result from the above information and instructions.