

Sylac

Varnish & Coatings for wooden surfaces

1K Clear Nitro Parquet Putty Resin SN020

Datum revizije: 04/08/2020

Detalji proizvoda

Ime Proizvoda (kod)	1K Clear Nitro Parquet Putty Resin SN020 (SN020)
Tip Proizvoda	Nitrocelulozni 1K Binder za parket git
Aplikacija	unutrašnje drvene površine
Opis	Transparentni Parket Git Binder • Održava boju drveta parketa • Brzosušeci • Odlična elastičnost da izdrži pokrete na površini parketa • Stabilizuje drvenu površinu

Informacije o proizvodu

Uslovi nanošenja i sušenja	Između 15°C i 35°C
Skladištenje	Proizvod treba čuvati na temperaturi ispod 40°C na suvom mestu daleko od toplote ili sunca.
Aparat za aplikaciju	Špatula
Pakovanje	1 L, 5 L
Rok trajanja	24 meseci. Nakon dužeg perioda skladištenja obezbedite homogenost proizvoda tako što ćete dobro promešati pre upotrebe da biste uklonili eventualni sediment.

Aplikacija

Priprema	Obrusite i očistite drvenu površinu od prašine, prljavštine, masti ili voska.						
Procedura mešanja	<table><tr><td>Proizvod</td><td>(kg)</td></tr><tr><td>SN 020</td><td>100</td></tr><tr><td>Wood Dust</td><td>17</td></tr></table>	Proizvod	(kg)	SN 020	100	Wood Dust	17
Proizvod	(kg)						
SN 020	100						
Wood Dust	17						
Aplikacija	Korak 1: Kombinujte 100 grama gita SN020 sa 17 grama drvene prašine i dobro promešajte. Nanošenje 1 sloj - Za tanke pukotine Vreme sušenja i ponovnog premaza: 1-2 sata u zavisnosti od uslova sušenja 2-3 Primena slojeva - Za debele pukotine Vreme sušenja i ponovnog premaza: 4-12 sati u zavisnosti od uslova sušenja. Za najbolje rezultate preporučuje se nanošenje sledećeg sloja osnovnog premaza sledećeg dana. Nakon što se git za parket potpuno osuši, možete naneti osnovni premaz za parket (tip SN100).						

Tehnički podaci

Čvrste materije	7.0 % ±1 (EN ISO 3251:2003)
Viskoznost	800 cPs ± 150 (EN ASTM D 2196)

The above information is given in good faith based on everything we know about the specific product. Every applier must take upon him to test the above information according to their personal work requirements before the application of the product. Sylac S.A. does not carry any responsibility for any damage that can result from the above information and instructions.