

## CP 999



Binder za ušpricavanje

Smola za ušpricavanje je jednokomponentni proizvod koji se koristi za farbanje karoserija automobila. Namenjen je balansiranju razlike u boji između specijalnog premaza 1K prajmera i stare površine premaza na okolnim elementima automobila (ili na istom elementu u slučaju farbanja).

Nakon nanošenja smole CP 999, specijalni premaz 1K za ušpricavanje treba naneti tehnikom mokro na mokro.

Sa svojim jedinstvenim svojstvima, CP 999 ne stvara efekat oblaka na ivicama nanetog sloja premaza i čini razliku neprimetnom.

| Pakovanje |                 |
|-----------|-----------------|
| Jedinica  | Zbirno (Kutija) |
| 1 L       | 3 kom           |



**100 jedinica CP 999,**  
**100 jedinica razređivača CP 048.**



Naneti mokro na mokro. Pištolj za farbanje\*.  
Otvaranje mlaznice pneumatskom metodom: **1.3-1.4 mm.**  
Radni pritisak – Visoki pritisak: **4 bar\***; HVL P: **2 bar\***.

\* Koristite opremu visokog pritiska i HVL P. Pritisak prema preporuci proizvođača pištolja.

#### Priprema površine:

Očistite površinu sredstvom za uklanjanje silikona.  
Očistite mat površinu sivom ili zlatnom abrazivnom podlogom, poželjno uz dodatak paste za matiranje.

#### Pokrivnost:

7-8 m<sup>2</sup>/l (sloj 40 μm)

#### Rok trajanja:

24 meseca (u originalnom neotvorenom pakovanju)

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products - according to the technical data sheet and execute the sample spray prior to target painting.